

Optran® UVWFS broadband fiber

Silica/silica fibers for applications from UV-C to IR-B

CeramOptec® is glad to offer a new extremely low loss fiber for the 200 nm to 2000 nm wavelength range. UVWFS fiber owns properties of UV and WF fibers and can be used for a variety of applications.

Wavelength


Optran® UVWFS 200–2000 nm

Numerical aperture (NA)

Low	0,12 ± 0,02 0,15 ± 0,02
Standard	0,22 ± 0,02
High	0,26 ± 0,02 0,28 ± 0,02

Advantages

- Low losses @ range 200 nm - 2000 nm
- Any value of NA from 0,12 to 0,28 available upon request
- Very low NA expansion
- Biocompatible material
- Manufactured at ISO 9001 compliant facility



Technical data

Wavelength / spectral range	Optran® UVWFS: 200 – 2000 nm
Numerical aperture (NA)	0,12 ± 0,02 0,15 ± 0,02 0,22 ± 0,02 0,26 ± 0,02 0,28 ± 0,02 or customised
Operating temperature	-190 to +350 °C
Glass diameter	Available from 100 to 300 µm standard 220 µm 660 µm coming soon
Standard core / cladding ratios	1:1,06 1:1,1 1:1,2 1:1,4 or customised
Standard proof test	70 kpsi (polyimide jacket)
Minimum bending radius	50 × cladding diameter (short-term mechanical stress) 300 × core diameter (during use with high laser power)

Headquarter


CeramOptec® GmbH, Siemensstr. 44, 53121 Bonn, Germany
Sales / Development, Brühler Straße 30, 53119 Bonn, Germany
 Phone: +49.228.979 670, Fax: +49.228.979 6799
 sales@ceramoptec.com, www.ceramoptec.com

Production sites

CeramOptec® GmbH Brühler Straße 30, 53119 Bonn, Germany
 CeramOptec® SIA Domes iela 1a, 5316 Livani, Latvia

Attenuation values

The following diagrams provide an overview of attenuation values relative to the wavelengths:



Applications

Ceram Optec® UVWFS optical fiber is the first choice for many applications where different types of fibers are needed simultaneously: spectroscopy, analytical instruments, sensing applications, astronomy, aerospace and avionics, military applications and many more.

Headquarter

CeramOptec® GmbH, Siemensstr. 44, 53121 Bonn, Germany
Sales / Development, Brühler Straße 30, 53119 Bonn, Germany
 Phone: +49.228.979 670, Fax: +49.228.979 6799
sales@ceramoptec.com, www.ceramoptec.com

Production sites

CeramOptec® GmbH Brühler Straße 30, 53119 Bonn, Germany
 CeramOptec® SIA Domes iela 1a, 5316 Livani, Latvia